



---

**DATA SHEET**  
**ALTOFLEX® LDX 0921**

---

**Description:** Blown Film applications

---

**Applications:**

---

- Trash bags
- Masking films
- Liners

<b>Resin Properties</b>	<b>Method</b>	<b>Typical Value</b>
Density	ASTM D1505	0.92 g/cm <sup>3</sup>
Melt Index, 190/2.16	ASTM D1238	2.1 g/10 min
Melting Point	ASTM D3418	107 °C
Vicat Softening Temperature	ASTM D1525	96 °C
<b>Film Properties</b>	<b>Method</b>	<b>Typical Value</b>
COF	ASTM D1894	> 1.00
Dart Drop Impact	ASTM D1709	90 g/mil
Elmendorf Tear MD TD	ASTM D1922	175 g/mil 120 g/mil
<b>Optical Properties</b>	<b>Method</b>	<b>Typical Value</b>
Haze	ASTM D1003	8.5%
Gloss, 60°	ASTM D2457	85

---

**Note:**

Typical properties: these results are not to be construed as specifications. The user must confirm the results by their own methods.

---